

Certificate of Analysis

Client

E&O Laboratories Ltd
Burnhouse
Bonnybridge
Scotland
FK4 2HH



E&O Laboratories Ltd

Sample: PP3044-P090 COLOREX Staph aureus

Batch Number: 00025093

Expiry Date: 28/04/2026

Date Received: 18/03/2026

Date Tested: 18/03/2026

Date of Issue: 23/03/2026

Sample Condition: Satisfactory

Burnhouse, Bonnybridge
Scotland, FK4 2HH
Telephone: 01324 840404
Fax:01324 841314
Email: info@eolabs.com

The RGI is a calculation of the % growth on the test media compared with the growth on a control media. The test medium must achieve an RGI between 70-120% for non-selective media / $\geq 50\%$ for selective media.
Accredited Test Method: ED/SOP/008 Quantitative evaluation using spread inoculum technique (solid media)

Productivity	RGI (%)	Colonial Appearance	Colonial Appearance Specification
S.aureus NCTC 12981	84	Mauve colonies	Mauve colonies

Accredited Test Method: ED/SOP/051 - log reduction of inoculum using drop inoculum for selective agar and fluid media. Inhibition indicates selectivity factor ≥ 2 .

Selectivity	Test Result	Specification
S.epidermidis NCTC 13360	Inhibited	Inhibited
E.faecalis NCTC 12697	Inhibited	Inhibited

Physical	Result	Specifications	Accredited Test Method
Sterility	Conforms	Within acceptable limits	ED/SOP/005 Visual check and growth assessment following incubation for 3 days at 15-25°C and 37°C
Sterility sampling is performed in accordance with ISO 2859-1:1999*. The inspection level is $\geq 0.4\%$ of the batch and the reject level ≤ 7 units depending on batch size			
pH	6.8	6.9 \pm 0.2	ED/SOP/003 measurement by pH meter

Certificate of Analysis

Client

E&O Laboratories Ltd
Burnhouse
Bonnybridge
Scotland
FK4 2HH



E&O Laboratories Ltd

Sample: PP3044-P090 COLOREX Staph aureus

Batch Number: 00025093

Expiry Date: 28/04/2026

Date Received: 18/03/2026

Date Tested: 18/03/2026

Date of Issue: 23/03/2026

Sample Condition: Satisfactory

Burnhouse, Bonnybridge
Scotland, FK4 2HH
Telephone: 01324 840404
Fax:01324 841314
Email: info@eolabs.com

Colour	Conforms	Straw4001C	ED/SOP/009 by visual observation. Range measured using Pantone® 4 colour process guide
Fill Quantity	Conforms	18-22ml	ED/SOP/054 by gravimetric determination
Moisture	Conforms	92 ± 1%	ED/SOP/053 with drying and gravimetric determination

All of the results on this certificate of analysis relate only to the samples submitted.

Test specifications are based on ISO 11133:2014/Amd/:2020 and internal product specifications.

*Sterility sampling is outwith scope of accreditation.



1894

Douglas Cameron
Technical Manager, E&O Laboratories Ltd